

# ELİT TAVAN

## PRODUCT DESCRIPTION

It is a water-based, high coverage, extra white, odorless, odorless acrylic resin, anti-fungal and anti-mold, matt interior ceiling paint.

### AREAS OF USE

<image>

Interior, Ceiling surfaces, Cement based plasters, Molded concrete, Plaster, Gypsum board, Sanded surfaces.

#### APPLICATION

**Surface Preparation:** Before application, surfaces should be cleaned from dirt, dust, old paint and free particles by mechanical means. Cracks and pits should be filled with ISOWEIR putty to achieve an optically uniform surface.

**Product Preparation and Application:** Mix before thinning. ISOWEIR ELİT CEILING should be diluted with clean water. After 4-6 hours, ISOWEIR ELİT CEILING is applied in 2 coats to the surfaces after surface preparation and priming, waiting for drying time between coats.

# FEATURES, ADVANTAGES

- It is odorless.
- Extra white, non-yellowing.
- High covering power.
- Low VOC.
- It prevents the formation of fungus and mold.



#### Star Boya ve Kimya San. ve Tic. Ltd. Şti.

ISISO Sanayii Sitesi A Blok No : 12 Hadımköy, İstanbul, Türkiye +90 (212) 623 2716 info@isoweir.com



- Leaves no brush and roller marks.
- Easy application and spreading.
- No cracking, blistering and flaking.

#### HEALTH AND SAFETY INFORMATION

- Please consider the hazard and precautionary statements indicated on the product packaging.
- Follow the guidelines specified in the product's safety data sheet.
- In case of unexpected health issues, consult the nearest healthcare facility.

# TECHNICAL SPECIFICATIONS

Color	_
Gloss	Matte (TS EN ISO 2813)
Appearance	_
Density (20 °C)	1,65 – 1,70 gr/cm <sup>3</sup> (TS EN ISO 2811)
Solid Matter (% Weight)	%62 ± 65 (ASTM D 4209)
Viscosity (25 °C)	12000-14000 cPs (ASTM D 2196)
PH (25 °C)	8-9 (ASTM E 70)
Elongation at Break	-
Water Transmission Rate	-
Application Temperature (°C)	5 °C – 30 °C
Application Apparatus	Roller, brush, spraying apparatus
Thinning Rate	%15 - %20
Amount of Use m²/kg	0,125 – 0,165 kg (single coat)
Drying Time (20 °C)	Initial Curing: 40 - 60 minutes Waiting time between coats: 3 hours Full Curing: 6 hours
Packaging	17,5 kg – 10 kg – 3,5 kg Plastic bucket
Storage Temperature	It should be stored in a place not exposed to direct sunlight, protected from frost, in closed packaging at 5 °C - 35 °C.
Storage Duration	1 Year
Quality Certificate	ISO 9001 – TS 5808



**Star Boya ve Kimya San. ve Tic. Ltd. Şti.** ISISO Sanayii Sitesi A Blok No : 12 Hadımköy, İstanbul, Türkiye +90 (212) 623 2716 info@isoweir.com