

YOL VE ZEMİN BOYASI

PRODUCT DESCRIPTION

It is a high performance semi-matte road and floor paint made of sb pure acrylic emulsion resin, resistant to different climatic conditions, U/V, high friction resistance.



AREAS OF USE

Asphalt surfaces, Painting of paving stones, Parking lot markings and floors, Walkways

APPLICATION

Surface Preparation: Application surfaces should be mechanically cleaned from dirt, dust, oil and free particles and should be dry.

Product Preparation and Application: The product is ready to use in its packaging. Thinning is not performed. It should be mixed well before use. The temperature of the asphalt or mineral substrate should be between +10°C - 30°C, the relative humidity should not be above 50% and the asphalt should be dry.

FEATURES, ADVANTAGES

- It has high friction resistance.
- It has U/V resistance.
- It has high tensile strength at break.



Star Boya ve Kimya San. ve Tic. Ltd. Şti.
ISISO Sanayii Sitesi A Blok No : 12 Hadımköy, İstanbul, Türkiye
+90 (212) 623 2716
info@isoweir.com



HEALTH AND SAFETY INFORMATION

- Please consider the hazard and precautionary statements indicated on the product packaging.
- Follow the guidelines specified in the product's safety data sheet.
- In case of unexpected health issues, consult the nearest healthcare facility.

TECHNICAL SPECIFICATIONS

Color	Ral colors
Gloss	Semi-matte
Appearance	-
Density (20 °C)	1,30 – 1,35 kg / lt
Application Temperature (°C)	+10.+30 °C / 50% humidity
Application Apparatus	Airless systems, pneumatic systems, roller, brush
Thinning Rate	None
Amount of Use m²/kg	0,600- 0,700 kg
Drying Time (20°C) (300-350 microns)	Initial Curing: 20 - 30 minutes Base Curing: 60 minutes The time may be longer in high humidity and low temperatures.
Packaging	20 kg Plastic bucket
Storage Temperature	It should be stored in a place not exposed to direct sunlight, protected from frost, in closed packaging at 5 °C - 35 °C. Protect from frost. If the product freezes, even if it is subsequently heated, it loses its properties and cannot be used again.
Storage Duration	1 Year
Quality Certificate	ISO 9001

