

# SU BAZLI PANEL KAPI

## PRODUCT DESCRIPTION

It is a modified pure acrylic resin based, water-based, wipeable, semi-matte panel door paint that allows panel doors to be renewed without changing their texture appearance.

## AREAS OF USE

Panel doors, moldings, veneer skirting boards.

## APPLICATION

**Surface Preparation:** The application area should be cleaned from oil and dirt with a damp cloth. The surface must be dry and clean.

**Product Preparation and Application:** Thinning is not recommended. Apply 2 or 3 coats on surfaces. Wait 2-3 hours between coats. Ambient temperature and humidity can change this time.

## FEATURES, ADVANTAGES

- ◆ It has a high covering power.
- ◆ It is long lasting.
- ◆ High U/V resistance, non-yellowing.
- ◆ It is odorless.
- ◆ It provides high protection.



## HEALTH AND SAFETY INFORMATION

- ◆ Please consider the hazard and precautionary statements indicated on the product packaging.
- ◆ Follow the guidelines specified in the product's safety data sheet.
- ◆ In case of unexpected health issues, consult the nearest healthcare facility.

## TECHNICAL SPECIFICATIONS

Color	In desired color
Gloss	Semi-matte
Appearance	-
Density (20 °C)	1,10 – 1,20 gr/cm <sup>3</sup> (TS EN ISO 2811)
Solid Matter (% Weight)	%75 ± 78 (ASTM D 4209)
Viscosity (25 °C)	-
PH (25 °C)	8-9 (ASTM E 70)
Elongation at Break	-
Water Transmission Rate	-
Application Temperature (°C)	5 °C – 30 °C
Application Apparatus	Brush, roller
Thinning Rate	%20 – %30
Amount of Use m <sup>2</sup> /kg	0,070 lt – 0,100 lt (single coat)
Drying Time (20 °C)	Initial Curing: 60 - 90 minutes Waiting time between coats: 2-3 hours Full Curing: 24 hours
Packaging	2,5 kg Plastic bucket
Storage Temperature	It should be stored in a place not exposed to direct sunlight, protected from frost, in closed packaging at 5 °C – 35 °C.
Storage Duration	1 Year
Quality Certificate	ISO 9001



**Star Boya ve Kimya San. ve Tic. Ltd. Şti.**

ISISO Sanayii Sitesi A Blok No : 12 Hadımköy, İstanbul, Türkiye  
+90 (212) 623 2716  
info@isoweir.com