

# TRANSFER ASTAR

## PRODUCT DESCRIPTION

It is a water-based, acrylic copolymer resin based, alkyd resin based (oil) paint conversion primer that enables the application of water-based paint on alkyd resin based (oil) paints.

## AREAS OF USE

It allows the application of water-based paints on old painted surfaces painted with solvent-based (oil) satin paint. It is used to increase the covering power when applying water-based paint to old water-based painted surfaces.

## APPLICATION

**Surface Preparation:** Surfaces should be cleaned from oil, dirt, dust and free particles by mechanical means before application. Old solvent-based paint surfaces should be abraded by sanding.

**Product Preparation and Application:** Apply 2 coats of ISOWEIR TRANSFER PRIMER to the purified old painted surface. ISOWEIR TRANSFER PRIMER should be applied by waiting 24 hours on old solvent-based surfaces and 4 hours on water-based surfaces between coats.



## FEATURES, ADVANTAGES

- ◆ It provides strong adhesion when applying water-based paint on old solvent-based paint.
- ◆ It provides strong adhesion in the application of water-based paints on old water-based paints.
- ◆ It is odorless.
- ◆ Easy to apply.
- ◆ It has high adhesion strength.

## HEALTH AND SAFETY INFORMATION

- ◆ Please consider the hazard and precautionary statements indicated on the product packaging.
- ◆ Follow the guidelines specified in the product's safety data sheet.
- ◆ In case of unexpected health issues, consult the nearest healthcare facility.

## TECHNICAL SPECIFICATIONS

Color	Transparent
Gloss	-
Appearance	Viscous liquid
Density (20 °C)	1,55 – 1,60 gr/cm <sup>3</sup> (TS EN ISO 2811)
Solid Matter (% Weight)	%68 – 70 (ASTM D 4209)
PH (25 °C)	8-9 (ASTM E 70)
Application Temperature (°C)	5 °C – 30 °C
Application Apparatus	Brush, roller
Thinning Rate	%10
Amount of Use m <sup>2</sup> /kg	0,100 lt – 0,150 lt (single coat)
Drying Time (20 °C) On Water Based Paint	Waiting time between coats: 6 hours Full Curing: 6 hours
Drying Time (20 °C) On Solvent Based Paint	Waiting time between coats: 24 hours Full Curing: 24 hours
Packaging	20 lt – 3,5 lt Plastic bucket
Storage Temperature	It should be stored in a place not exposed to direct sunlight, protected from frost, in closed packaging at 5 °C - 35 °C.
Storage Duration	1 Year
Quality Certificate	ISO 9001



**Star Boya ve Kimya San. ve Tic. Ltd. Şti.**

ISISO Sanayii Sitesi A Blok No : 12 Hadımköy, İstanbul, Türkiye

+90 (212) 623 2716

info@isoweir.com

www.isoweir.com