

# STRENAC

## PRODUCT DESCRIPTION

It is a strenacrylic copolymer resin based, flat, flexible, exterior paint.

### AREAS OF USE

It is used on building exteriors, concrete, plaster, brick etc. surfaces.



### APPLICATION

**Surface Preparation:** The surface should be cleaned from dust, dirt and free particles by mechanical methods. Deep cracks should be filled with cement plasters with ISOWEIR LSK additives to ensure optical uniformity. ISOWEIR FIXATOR should be applied in a single coat on all surfaces. (The surface should be moisturized at high temperatures).

**Product Preparation and Application:** It is applied to the prepared surfaces in 2 coats, waiting for drying time between coats.

#### FEATURES, ADVANTAGES

- High resistance to atmospheric conditions, high protection.
- It has high alkali resistance.
- High U/V resistance.
- It does not prevent vapor diffusion.
- It does not swell, crack or flack due to its high adhesion and strong bond structure.
- Low VOC (in accordance with European Union norms VOC values).
- It has high salt vapor resistance in coastal areas.



Star Boya ve Kimya San. ve Tic. Ltd. Şti. ISISO Sanayii Sitesi A Blok No : 12 Hadımköy, İstanbul, Türkiye +90 (212) 623 2716 info@isoweir.com



# HEALTH AND SAFETY INFORMATION

- Please consider the hazard and precautionary statements indicated on the product packaging.
- Follow the guidelines specified in the product's safety data sheet.
- In case of unexpected health issues, consult the nearest healthcare facility.

#### TECHNICAL SPECIFICATIONS

Color	In desired color
Gloss	Matte (TSE EN ISO 2813)
Appearance	-
Density (20 °C)	1,45 – 1,48 gr/cm³ (TS EN ISO 2196)
Solid Matter (% Weight)	%65 ± 68 (ASTM D 4209)
PH (25 °C)	8-9 (ASTM E 70)
Application Temperature (°C)	5 °C - 30 °C
Application Apparatus	Brush, roller
Thinning Rate	%10 - %15
Amount of Use m²/kg	0,100 kg - 0,125 kg (single coat)
Drying Time (20 °C)	Surface drying: 30 minutes Second Coat Application: 2-3 hours Full Curing: 24 hours
Packaging	20 kg Plastic bucket
Storage Temperature	It should be stored in a place not exposed to direct sunlight, protected from frost, in closed packaging at 5 °C - 35 °C.
Storage Duration	1 Year
Quality Certificate	ISO 9001 – TS 7847



info@isoweir.com